



## Interlam EcoGloss™ 65μ (2.6 mil)

### Product Description

Interlam EcoGloss™ 65μ is a 40μ (1.6mil) gloss finish polypropylene overlaminating film coated on one side with a pressure sensitive, aqueous acrylic adhesive which is protected by a bleached Kraft green grid release paper coated on one side with siliconised polyethylene. Available in various sizes.

### Suggested Applications

Interlam EcoGloss™ 65μ is particularly suitable for POP displays, short-term indoor signage, architectural renderings, maps and other indoor promotional graphics to be used under direct light. This product is not recommended for laminating vinyl banners or other applications where the laminate will be required to expand and contract with the print media.

### Product Structure

Film:	Polypropylene	^ . . . ^ (2.6 mil) v . . . v 65μ
Adhesive:	Aqueous Acrylic (Pressure Sensitive)	
Release Liner:	1 Side PE coated bleached Kraft Green Grid Paper (Moisture Stable)	

### General Properties

Film Thickness	40μ (1.6mil)
Adhesive Layer	25μ (1mil)
Ratio Film/Adhesive	1.6/1
UV Protection Factor	Film contains some U.V. stabilisers, which prevent film degradation, but should be used for indoor applications only.
Outdoor Durability	Not Applicable
Heat Resistance Range	110°C – 120°C (230°F – 248°F)
Peel Strength (20 min, FTM1)	23 N/25mm

### Process Settings

Roller Laminator	Press
Temperature: Room temperature to 49°C (120°F) Speed: 0.3m to 1.75m (1 ft to 6 ft) per minute	NOT RECOMMENDED

Specifications subject to change without notice.

Published information concerning Drytac products is based upon research which the company believes to be reliable and accurate. Such information is intended only as a guide and is given without guarantees. Purchasers should independently determine, prior to use, the suitability of each material for their specific purpose. Drytac does not accept liability for risks associated with the performance of the materials in application. All Drytac products are subjected to carefully quality control throughout the manufacturing process and are sold subject to Drytac standard conditions of sale

Drytac Europe Ltd (UK) – Drytac House, Filwood Road, Fishponds, Bristol, BS16 3RY, UK. Tel: +44 (0) 845-070-0660

Drytac Corp. (USA) – 5383 Glen Alden Drive, Richmond, Virginia 23231, USA. Telephone: 1-800-603-6610

Drytac Canada Inc. (Canada) – 220 Caldari Road, Concord, Ontario, L4K 3X5, Canada. Telephone: 1-800-353-288