



Interlam EcoTex™ 165μ (6.6 mil)

Product Description

Interlam EcoTex™ 165μ is a 140μ (5.6 mil) pebble textured clear polypropylene overlaminating film coated on one side with a pressure sensitive, aqueous acrylic adhesive which is protected by a bleached Kraft green grid release paper coated on one side with siliconised polyethylene. Available in various sizes.

Suggested Applications

Interlam EcoTex™ 165μ is an ideal film for laminating mounted prints that will be placed in high-traffic indoor display areas. It is also suitable for laminating mouse mats and other similar applications.

Product Structure

Film:	Pebble Textured Polypropylene	^ v (6.6 mil) 165μ
Adhesive:	Aqueous Acrylic (Pressure Sensitive)	
Release Liner:	1 Side PE coated bleached Kraft Green Grid Paper (Moisture Stable)	

General Properties

Film Thickness	140μ (5.6mil)
Adhesive Layer	25μ (1mil)
Ratio Film/Adhesive	5/1
UV Protection Factor	Film is UV stable and provides some U.V. protection to the underlying image.
Outdoor Durability	Not Applicable
Heat Resistance Range	70°C to 95°C (158°F to 203°F)
Peel Strength (20 min, FTM1)	23 N/25mm

Process Settings

Roller Laminator	Press
Temperature: Room temperature to 49°C (120°F) Speed: 0.3m to 1.75m (1 ft to 6 ft) per minute	NOT RECOMMENDED

Specifications subject to change without notice.

Published information concerning Drytac products is based upon research which the company believes to be reliable and accurate. Such information is intended only as a guide and is given without guarantees. Purchasers should independently determine, prior to use, the suitability of each material for their specific purpose. Drytac does not accept liability for risks associated with the performance of the materials in application. All Drytac products are subjected to carefully quality control throughout the manufacturing process and are sold subject to Drytac standard conditions of sale

Drytac Europe Ltd (UK) – Drytac House, Filwood Road, Fishponds, Bristol, BS16 3RY, UK. Tel: +44 (0) 845-070-0660

Drytac Corp. (USA) – 5383 Glen Alden Drive, Richmond, Virginia 23231, USA. Telephone: 1-800-603-6610

Drytac Canada Inc. (Canada) – 220 Caldari Road, Concord, Ontario, L4K 3X5, Canada. Telephone: 1-800-353-288