



## Interlam Pro Glossy™ UV 75µ (3 mil)

### Product Description

Interlam Pro Glossy™ UV 75µ is a 50µ (2 mil) gloss finish, plasticised, UV stabilised, clear PVC overlaminating film coated on one side with a pressure sensitive, aqueous acrylic adhesive which is protected by a bleached Kraft release paper coated on both sides with polyethyleneone side siliconised. Available in various sizes.

### Suggested Applications

Interlam Pro Glossy laminating film is perfectly suited for internal and external use on flexible media and substrates wherever a gloss finish is required.

### Product Structure

|                |   |  |
|----------------|---|--|
| Film:          | Gloss PVC   |  |
| Adhesive:      | Aqueous Acrylic (Pressure Sensitive)                    |  |
| Release Liner: | 2 Side PE coated bleached Kraft Paper (Moisture Stable) |  |

### General Properties

|                              |   |
|------------------------------|---|
| Film Thickness               | 50 µ (2 mil)  |
| Adhesive Layer               | 25 µ (1 mil)  |
| Ratio Film/Adhesive          | 2/1   |
| UV Protection Factor         | Film contains U.V. stabilisers, which prevent film degradation and provides some U.V. protection to the underlying image. |
| Outdoor Durability           | 12 months without discernable change.   |
| Heat resistance              | 70°C to 95°C (158°F to 203°F)   |
| Peel Strength (20 min, FTM1) | 23 N/25mm   |

### Process Settings

|  |                                 |
|--|---------------------------------|
| <b>Roller Laminator</b><br>Temperature: Room temperature to 49°C (120°F)<br>Speed: 0.3m to 1.75m (1 ft to 6 ft) per minute | <b>Press</b><br>NOT RECOMMENDED |
|--|---------------------------------|

Specifications subject to change without notice.

Published information concerning Drytac products is based upon research which the company believes to be reliable and accurate. Such information is intended only as a guide and is given without guarantees. Purchasers should independently determine, prior to use, the suitability of each material for their specific purpose. Drytac does not accept liability for risks associated with the performance of the materials in application. All Drytac products are subjected to carefully quality control throughout the manufacturing process and are sold subject to Drytac standard conditions of sale

Drytac Europe Ltd (UK) – Drytac House, Filwood Road, Fishponds, Bristol, BS16 3RY, UK. Tel: +44 (0) 845-070-0660  
 Drytac Corp. (USA) – 5383 Glen Alden Drive, Richmond, Virginia 23231, USA. Telephone: 1-800-603-6610  
 Drytac Canada Inc. (Canada) – 220 Caldari Road, Concord, Ontario, L4K 3X5, Canada. Telephone: 1-800-353-288