



## Interlam Pro Matt™ UV 100µ (4 mil)

### Product Description

Interlam Pro Matt™ UV 100µ is a 75µ (3 mil) plasticised, embossed, UV stabilised, matt finish, clear PVC overlaminating film coated on one side with a pressure sensitive, aqueous acrylic adhesive which is protected by a bleached Kraft release paper coated on both sides with polyethylene one side siliconised. Available in various sizes.

### Suggested Applications

Interlam Pro Matt™ is recommended for situations internally and externally where a non-glare finish is required or where specific lighting conditions cannot be controlled. It is ideal for images such as exhibitions and pop-up displays that will be viewed under direct lighting from many different angles.

### Product Structure

Film:	Matt PVC	
Adhesive:	Aqueous Acrylic (Pressure Sensitive)	
Release Liner:	2 Side PE coated bleached Kraft Paper (Moisture Stable)	

### General Properties

Film Thickness	75µ (3mil)
Adhesive Layer	25µ (1mil)
Ratio Film/Adhesive	3/1
UV Protection Factor	Film contains U.V. stabilisers, which prevent film degradation and provides some U.V. protection to the underlying image.
Outdoor Durability	12 months without discernable change
Heat resistance	70°C to 95°C (158°F to 203°F)
Peel Strength (20 min, FTM1)	23 N/25mm

### Process Settings

<b>Roller Laminator</b> Temperature: Room temperature to 49°C (120°F) Speed: 0.3m to 1.75m (1 ft to 6 ft) per minute	<b>Press</b> NOT RECOMMENDED
--	---------------------------------

Specifications subject to change without notice.

Published information concerning Drytac products is based upon research which the company believes to be reliable and accurate. Such information is intended only as a guide and is given without guarantees. Purchasers should independently determine, prior to use, the suitability of each material for their specific purpose. Drytac does not accept liability for risks associated with the performance of the materials in application. All Drytac products are subjected to carefully quality control throughout the manufacturing process and are sold subject to Drytac standard conditions of sale

Drytac Europe Ltd (UK) – Drytac House, Filwood Road, Fishponds, Bristol, BS16 3RY, UK. Tel: +44 (0) 845-070-0660  
 Drytac Corp. (USA) – 5383 Glen Alden Drive, Richmond, Virginia 23231, USA. Telephone: 1-800-603-6610  
 Drytac Canada Inc. (Canada) – 220 Caldari Road, Concord, Ontario, L4K 3X5, Canada. Telephone: 1-800-353-288