



MediaShield Canvastex™ UV 225µ (9 mil)

Product Description

MediaShield Canvastex™ UV 225µ (9 mil) is a 200µ (8 mil) plasticised, embossed, UV stabilised, canvas finish, clear PVC overlaminating film coated on one side with a heat activated solvent acrylic adhesive, which is protected by a bleached Kraft grey grid release paper coated on one side with siliconised polyethylene. Available in various sizes.

Suggested Applications

MediaShield Canvastex™ UV can be used as an alternative to mounting canvas. Simply laminating your print with this film will offer the illusion that the image has been transferred to a coarse canvas. It is highly recommended for photographs, posters and fine art inkjet prints.

Product Structure

Film:	Canvas textured PVC	225µ (9 mil)
Adhesive:	Solvent Acrylic (Heat Activated)	
Release Liner:	1 Side PE coated bleached Kraft Grey Grid Paper (Moisture Stable)	

General Properties

Film Thickness	200µ (8 mil)
Adhesive Layer	25µ (1mil)
Ratio Film/Adhesive	8/1
UV Protection Factor	Film contains U.V. stabilisers, which prevent film degradation and provides some U.V. protection to the underlying image.
Outdoor Durability	3 months will only show inconsequential changes in properties of this product.
Heat Resistance Range	70°C to 95°C (158°F to 203°F)
Peel Strength (20 min, FTM1)	18 N/25mm

Process Settings

Roller Laminator	Press
Temperature: 85°C to 102°C (185°F to 215°F) Speed: 0.3m to 2.5m (1 ft to 8 ft) per minute	NOT RECOMMENDED

Specifications subject to change without notice.

Published information concerning Drytac products is based upon research which the company believes to be reliable and accurate. Such information is intended only as a guide and is given without guarantees. Purchasers should independently determine, prior to use, the suitability of each material for their specific purpose. Drytac does not accept liability for risks associated with the performance of the materials in application. All Drytac products are subjected to carefully quality control throughout the manufacturing process and are sold subject to Drytac standard conditions of sale

Drytac Europe Ltd (UK) – Drytac House, Filwood Road, Fishponds, Bristol, BS16 3RY, UK. Tel: +44 (0) 845-070-0660

Drytac Corp. (USA) – 5383 Glen Alden Drive, Richmond, Virginia 23231, USA. Telephone: 1-800-603-6610

Drytac Canada Inc. (Canada) – 220 Caldari Road, Concord, Ontario, L4K 3X5, Canada. Telephone: 1-800-353-288