



WindowTac™

Product Description

WindowTac™ is a visually clear 23mic Polyester film, coated one side with an removable aqueous adhesive, which is protected by an embossed liner which imparts an embossed pattern into the adhesive coating. The other side is coated with a permanent aqueous acrylic adhesive protected by a moisture stable release liner.

Suggested Applications

This product is recommended for the facemounting of graphics onto windows at location. The micro grooves that are imparted into the removable adhesive allow for easy air evacuation and application using a hand squeegee. The nature of the adhesive allows removal with no residue.

Product Structure

Release liner:	1 Side siliconised PE coated bleached Kraft Paper (Moisture Stable)
Adhesive layer:	Aqueous Acrylic (Pressure Sensitive) - Permanent
Film:	23 mic Clear Polyester
Adhesive layer:	Aqueous acrylic removable adhesive - ph neutral
Coreflute:	70mic textured filmic release liner

General Properties

Film Thickness	23mic (0.9mil)
Adhesive Layer	1 x 25mic + 1 x 15mic
Ratio Film/Adhesive	1/1
UV Protection Factor	Film contains U.V. stabilisers, which prevent film degradation and provides some U.V. protection to the underlying image.
Outdoor Durability	N/A
Heat resistance	70°C to 95°C (158°F to 203°F)
Peel Strength (20 min, FTM1)	22N/25mm2 (PERM) 5N/25mm2 (PEEL)

Process Settings

Roller Laminator	Press
Temperature: Room temperature to 49°C (120°F) Speed: 0.3m to 1.75m (1 ft to 6 ft) per minute	NOT RECOMMENDED

Specifications subject to change without notice.

Published information concerning Drytac products is based upon research which the company believes to be reliable and accurate. Such information is intended only as a guide and is given without guarantees. Purchasers should independently determine, prior to use, the suitability of each material for their specific purpose. Drytac does not accept liability for risks associated with the performance of the materials in application. All Drytac products are subjected to carefully quality control throughout the manufacturing process and are sold subject to Drytac standard conditions of sale

Drytac Europe Ltd (UK) – Drytac House, Filwood Road, Fishponds, Bristol, BS16 3RY, UK. Tel: +44 (0) 845-070-0660
Drytac Corp. (USA) – 5383 Glen Alden Drive, Richmond, Virginia 23231, USA. Telephone: 1-800-603-6610
Drytac Canada Inc. (Canada) – 220 Caldari Road, Concord, Ontario, L4K 3X5, Canada. Telephone: 1-800-353-288

