



## BestMount™ DS Plus

### Product Description

BestMount™ is a 75µ (3 mil) white polypropylene mounting film coated on both sides with a pressure sensitive, aqueous acrylic adhesive which is protected by a bleached Kraft differential release paper (moisture stable) coated on both sides with siliconised polyethylene. Available in various sizes.

### Suggested Applications

BestMount™ is suited for mounting such products as pre-coating of boards and for image decal applications. The white polypropylene carrier is ideal for mounting thin output media to dark substrates, such as black Gatorfoam™.

### Product Structure

Adhesive:	Aqueous Acrylic (Pressure Sensitive)	135µ (5.3 mil)
Carrier:	White Polypropylene (OPP)	
Adhesive:	Aqueous Acrylic (Pressure Sensitive)	
Release Liner:	2 Side PE Coated Bleached Kraft Differential Release Paper	

### General Properties

Film Thickness	75µ (3 mil)
Adhesive Layer	30µ (1mil) on each side
Ratio Film/Adhesive	1.25/1
UV Protection Factor	Not Applicable
Outdoor Durability	Not Applicable
Heat Resistance Range	110°C to 120°C (230°F to 248°F)
Peel Strength (20 min, FTM1)	13 N/25mm

### Process Settings

Roller Laminator	Press
Temperature: Room temperature to 49°C (120°F) Speed: 0.3m to 2.5m (1 ft to 8 ft) per minute	NOT RECOMMENDED

Specifications subject to change without notice.

Published information concerning Drytac products is based upon research which the company believes to be reliable and accurate. Such information is intended only as a guide and is given without guarantees. Purchasers should independently determine, prior to use, the suitability of each material for their specific purpose. Drytac does not accept liability for risks associated with the performance of the materials in application. All Drytac products are subjected to carefully quality control throughout the manufacturing process and are sold subject to Drytac standard conditions of sale

Drytac Europe Ltd (UK) – Drytac House, Filwood Road, Fishponds, Bristol, BS16 3RY, UK. Tel: +44 (0) 845-070-0660

Drytac Corp. (USA) – 5383 Glen Alden Drive, Richmond, Virginia 23231, USA. Telephone: 1-800-603-6610

Drytac Canada Inc. (Canada) – 220 Caldari Road, Concord, Ontario, L4K 3X5, Canada. Telephone: 1-800-353-288