Facemount®

Facemount[®] is a 1 mil (25µ) high quality, optically clear PET film, coated on both sides with a pressure sensitive, permanent solvent acrylic adhesive, both of which are protected by a clear PET release liner. Facemount[®] is made using the finest optical clarity components. It offers excellent UV stability to graphic prints.

- RECOMMENDED FOR SECOND SURFACE MOUNTING (COMMONLY REFERRED TO AS FACE MOUNTING) OF IMAGES TO CLEAR SUBSTRATES, SUCH AS PETG[™], PLEXIGLAS[™], ACRYLIC, POLYCARBONATE, AND GLASS.
- IDEAL FOR LENTICULAR IMAGING APPLICATIONS, BACKLIT DISPLAY TRANSPARENCIES, TOUCH SCREEN DISPLAYS, AND HIGH QUALITY PHOTOGRAPHIC AND INKJET PRINTED IMAGES
- SUITABLE FOR INDOOR AND SHORT-TERM OUTDOOR USE

For more information, performance and warranty guide lines please contact your local Drytac office.

© 2018 Drytac Corporation. E&OE. All other trademarks are the property of their respective owners.

TECHNICAL SPECIFICATION

PRODUCT STRUCTURE

Release Liner	Siliconised 1 Side PET
Adhesive	Permanent Solvent Acrylic (Pressure Sensitive)
Film	Clear PET
Adhesive	Permanent Solvent Acrylic (Pressure Sensitive)
Release Liner	Siliconised 1 Side PET

PRODUCT CHARACTERISTIC

Film Thickness	1 mil (25µ) 2.8 mil
Adhesive Layer	0.9 mil (23µ)
Film/Adhesive Ratio	0.9:1:0.9
UV Protection Factor	UV Stable
Outdoor Durability	2 years
Peel Strength (20 min, FTM1)	12.8 N/25mm (glass 24 hours)
Service Temperature Range	-40°F to 212°F (-40°C to 100°C)
Shelf Life	2 Years
Storage Conditions	59°F to 72°F (15°C to 22°C); 50 - 55% Relative Humidity

PROCESS SETTING

Roller Laminator

Not Recommended

Press

Temperature: Room Temperature to 104°F (40°C) **Speed:** 1 ft to 8 ft (0.3m to 2.5m) per minute



Europe Filwood Road, Fishponds, Bristol, BS16 3RY, United Kingdom bristol@drytac.com Tel: +44 (0) 117 958 6500

Canada

105 Nuggett Court, Brampton, Ontario, L6T 5A9, Canada toronto@drytac.com Tel: +1 800.353.2883 USA

5601 Eastport Boulevard, Richmond, Virginia, 23231, USA customerservice@drytac.com Tel: +1 800.280.6013

www.drytac.com