

# Polar®

## Dynamic White RB

### with Interlam™ Pro Emerytex®

Polar® Dynamic is a 3.2 mil (80µ) white monomeric PVC film with either a gloss or matte finish. Polar® Dynamic is coated on one side with a grey removable, pressure sensitive solvent acrylic adhesive that is protected by a white Kraft release paper coated on both sides with PE and siliconized on the release side.

Interlam™ Pro Emerytex® is a 4 mil (100µ) monomeric soft calendared PVC laminating film with a matte pebble textured finish, coated on one side with a pressure sensitive acrylic adhesive that is protected by a bleached Kraft release paper coated on both sides with PE and siliconized on the release side.

- IDEAL FOR SHORT-TERM INDOOR FLOOR GRAPHICS
- THE PAIRED SOLUTIONS CARRIES SEVERAL SLIP RATINGS & CERTIFICATIONS



### Polar Dynamic White RB

(Eco) Solvent  
Latex  
UV



Widths up to 54in



UP TO  
**6** MONTHS DURABILITY  
INTERIOR\*

\* Up to 6 months indoor durability dependent upon floor-traffic and correct installation.

For more information, performance and warranty guidelines please contact your local Drytac office.

© 2020 Drytac Corporation. E&OE.  
All other trademarks are the property of their respective owners.

## PAIRED FLOOR GRAPHIC SOLUTION TECHNICAL SPECIFICATIONS

### Polar® Dynamic White RB

#### PRODUCT STRUCTURE

Film	Gloss or Matte White Monomeric PVC
Adhesive	Grey Removable Solvent Acrylic
Release Liner	135 gsm Siliconized 1 Side Bleached Clay Coated Kraft

### Polar® Dynamic White RB

#### PRODUCT CHARACTERISTICS

Film Thickness	3.2 mil (80µ)	4.2 mil (105µ)
Adhesive Layer	1.0 mil (25µ)	
Application Temperature	>50°F (10°C)	
Service Temperature Range	-5°F to 149°F (-20°C to 65°C)	

### Interlam™ Pro Emerytex®

#### PRODUCT STRUCTURE

Film	Matte Pebble Textured Monomeric PVC
Adhesive	Acrylic (Pressure Sensitive)
Release Liner	2 Side PE Coated, 1 Side Siliconised Kraft

### Interlam™ Pro Emerytex®

#### PRODUCT CHARACTERISTICS

Film Thickness	4 mil (100µ)	5 mil (125µ)
Adhesive Layer	1 mil (25µ)	
Fire Ratings	Class 0 (BS 476 Part 6 and 7) Class 1 or A (ASTM E-84)	
FDA Certification	PASS (FDA 21 CFR 177.1975)	
Slip Certifications	Low Slip Potential (EN 13036-4) R 11 (DIN 51130:2010) Dry: 62; Wet: 35 (HB198:2014 (AS/NZS 4586)) Acceptable (ANSI B101.3)	
Application Temperature	>-4°F (-20°C)	
Service Temperature Range	-4°F to 203°F (-20°C to 95°C)	

Shelf Life	1 year
Storage Conditions	59°F to 72°F (15°C to 22°C); 50 - 55% Relative Humidity

**DRYTAC®**  
ADHESIVE SCIENCE

www.drytac.com