

Interlam™ EcoTex™ is a 4.7 mil (120µ) PP laminating film with a pebble textured finish, coated on one side with a pressure sensitive, aqueous acrylic adhesive that is protected by a bleached Kraft release paper coated on one side with siliconized PE. Interlam™ EcoTex™ is phthalate-free and provides excellent image enhancement and moisture protection for indoor graphics.

- THE SCUFF-RESISTANT, PEBBLE TEXTURED FINISH MAKES THIS LAMINATING FILM SUITABLE FOR GRAPHICS WHERE EXTENSIVE HANDLING MAY BE INVOLVED
- IDEAL FOR LAMINATING AND ENCAPSULATING TRADESHOW AND BANNER STAND GRAPHICS, SIGNAGE IN HIGH TRAFFIC AREAS, COUNTER MATS, PLACEMATS, AND OTHER GRAPHICS WHERE A SCUFF-RESISTANT FINISH IS REQUIRED AND COST IS A KEY FACTOR
- IDEAL FOR SINGLE-SIDED LAMINATION DUE TO ITS DIMENSIONAL STABILITY
- OFFERS EXCELLENT UV PROTECTION FOR HIGH QUALITY IMAGES, PHOTOGRAPHIC PRINTS, WALLCOVERINGS, AND SELF-ADHESIVE VINYL

For more information, performance and warranty guidelines please contact your local Drytac office.

© 2020 Drytac Corporation. E&OE. All other trademarks are the property of their respective owners.

TECHNICAL SPECIFICATION

PRODUCT STRUCTURE

Film	Pebble Textured PP
Adhesive	Aqueous Acrylic (Pressure Sensitive)
Release Liner	Siliconised 1 Side PE Coated Kraft

PRODUCT CHARACTERISTICS

Film Thickness	4.7 mil (120µ) 5.7 mil
Adhesive Layer	1 mil (25µ) (145µ)
UV Protection	Yes
Outdoor Durability	Not Applicable
Service Temperature Range	-4°F to 248°F (-20°C to 120°C)
Peel Strength (20 min, FTM1)	11 N/25mm
Slip Ratings	<ul style="list-style-type: none"> ● EN 13036-4/ASTM E303: Low Slip Potential; Dry: 71 Moderate Slip Potential; Wet: 25 ● R10 (DIN 51130:2010)
Shelf Life	2 Years
Storage Conditions	59°F to 72°F (15°C to 22°C); 50 - 55% Relative Humidity

PROCESS SETTINGS

Equipment Type & Temperature	Speed
Roller Laminator Room temperature to 104°F (40°C)	1 ft to 8 ft (0.3m to 2.5m) per minute
Press	Not recommended

DRYTAC®

ADHESIVE SCIENCE

Europe

Filwood Road,
Fishponds,
Bristol, BS16 3RY,
United Kingdom
bristol@drytac.com
Tel: +44 (0) 117 958 6500

Canada

30 Driver Road,
Brampton,
Ontario, L6T 5V2,
Canada
toronto@drytac.com
Tel: +1 800.353.2883

USA

5401-B Eubank Road,
Sandston,
Virginia, 23150,
USA
customerservice@drytac.com
Tel: +1 800.280.6013