

Interlam™

Pro Emerytex®

Interlam™ Pro Emerytex® is a 4 mil (100µ) monomeric soft calendared PVC laminating film with a matte pebble textured finish, coated on one side with a pressure sensitive acrylic adhesive that is protected by a bleached Kraft release paper coated on both sides with PE and siliconised on the release side. Both the film and adhesive contain UV stabilisers, which protect against UV degradation. The anti-slip properties of Interlam™ Pro Emerytex® have been tested in accordance with DIN 51130 standards and have been awarded an R11 rating.

- RECOMMENDED FOR LAMINATING MOUNTED PRINTS THAT WILL BE PLACED IN HIGH TRAFFIC INDOOR AND OUTDOOR DISPLAY AREAS
- IDEAL FOR TRADESHOW GRAPHICS, POP DISPLAYS, MOUSE PADS, COUNTER MATS, EVENT SIGNAGE, FLOOR GRAPHICS, AND OTHER SIGNAGE WHERE A SCUFF-RESISTANT FINISH IS REQUIRED
- CAN BE COMBINED WITH DRYTAC'S PRINT MEDIA TO CREATE A SLIP-RESISTANT FLOOR GRAPHICS.
- FILM AND ADHESIVE CONTAIN UV STABILIZERS, WHICH PREVENT FILM DEGRADATION AND PROVIDE UV PROTECTION TO THE UNDERLYING IMAGE

PROCESS SETTINGS

Equipment Type & Temperature	Speed
Roller Laminator Room temperature to 104°F (40°C)	1 ft to 8 ft (0.3m to 2.5m) per minute
Press	Not recommended

For more information, performance and warranty guide lines please contact your local Drytac office.

© 2020 Drytac Corporation. E&OE. All other trademarks are the property of their respective owners.

TECHNICAL SPECIFICATION

PRODUCT STRUCTURE

Film	Matte Pebble Textured Monomeric Soft Calendared PVC
Adhesive	Acrylic (Pressure Sensitive)
Release Liner	2 Side PE Coated, 1 Side Siliconised Kraft

PRODUCT CHARACTERISTICS

Film Thickness	4 mil (100µ) 5 mil (125µ)
Adhesive Layer	1 mil (25µ) (125µ)
Outdoor Durability	5 Years (Ink Dependent)
Fire Ratings	Class 0 (BS 476 Part 6 and 7) Class 1 or A (ASTM E-84) PASS (CAN/ULC-S102)
Paired Solution Fire Rating	B _{f1} - s1 (EN 13501-1) when paired with Polar Grip print media
FDA Certification	PASS (FDA 21 CFR 177.1975)
Slip Certifications	R 11 (DIN 51130:2010) Dry: 62; Wet: 35 (HB198:2014 (AS/NZS 4586)) Acceptable (ANSI B101.3) Low Slip Potential; Dry: 64 Wet: 36 (EN 13036-4)
Application Temperature	>41°F (20°C)
Service Temperature Range	-4°F to 203°F (-20°C to 95°C)
Peel Strength (20 min, FTM1)	11 N/25mm
Shelf Life	2 years
Storage Conditions	59°F to 72°F (15°C to 22°C); 50 - 55% Relative Humidity

DRYTAC®

Europe

Filwood Road,
Fishponds,
Bristol, BS16 3RY,
United Kingdom
bristol@drytac.com
Tel: +44 (0) 117 958 6500

Canada

30 Driver Road,
Brampton,
Ontario, L6T 5V2,
Canada
toronto@drytac.com
Tel: +1 800.353.2883

USA

5401-B Eubank Road,
Sandston,
Virginia, 23150,
USA
customerservice@drytac.com
Tel: +1 800.280.6013