

InterlamTM

Pro Gloss

InterlamTM Pro Gloss is a 3 mil (75 μ) monomeric soft calendared PVC laminating film with a Gloss finish, coated on one side with a pressure sensitive, aqueous acrylic adhesive that is protected by a bleached Kraft release paper coated on both sides with PE and siliconized on the release side.

- RECOMMENDED FOR INTERIOR AND EXTERIOR USE ON FLEXIBLE MEDIA SUBSTRATES WHERE A GLOSS FINISH IS REQUIRED
- IDEAL FOR POP DISPLAYS, ARCHITECTURAL RENDERINGS, PROMOTIONAL DISPLAYS, EVENT SIGNAGE AND PHOTOGRAPHIC IMAGES

For more information, performance and warranty guidelines please contact your local Drytac office.

© 2019 Drytac Corporation. E&OE. All other trademarks are the property of their respective owners.

TECHNICAL SPECIFICATION

PRODUCT STRUCTURE

Film	Gloss Monomeric Soft Calendared PVC
Adhesive	Acrylic (Pressure Sensitive)
Release Liner	2 Side PE Coated, 1 Side Siliconized Kraft

PRODUCT CHARACTERISTICS

Film Thickness	3 mil (75 μ)	4 mil (100 μ)
Adhesive Layer	1 mil (25 μ)	
Film/Adhesive Ratio	3:1	
UV Protection Factor	Film contains UV stabilizers, which prevent film degradation and provide UV protection to the underlying image	
Outdoor Durability	5 Years (Ink Dependent)	
Fire Rating	Class 0	
Application Temperature	>41°F (20°C)	
Service Temperature Range	-13°F to 302°F (-25°C to 150°C)	
Peel Strength (20 min, FTM1)	11 N/25mm	
Shelf Life	2 Years	
Storage Conditions	59°F to 72°F (15°C to 22°C); 50 - 55% Relative Humidity	

PROCESS SETTINGS

Equipment Type & Temperature	Speed
Roller Laminator Room temperature to 104°F (40°C)	1 ft to 8 ft (0.3m to 2.5m) per minute
Press	Not recommended

DRYTAC[®]
ADHESIVE SCIENCE

Europe

Filwood Road,
Fishponds,
Bristol, BS16 3RY,
United Kingdom
bristol@drytac.com
Tel: +44 (0) 117 958 6500

Canada

30 Driver Road,
Brampton,
Ontario, L6T 5V2,
Canada
toronto@drytac.com
Tel: +1 800.353.2883

USA

5601 Eastport Boulevard,
Richmond,
Virginia, 23231,
USA
customerservice@drytac.com
Tel: +1 800.280.6013