

# Interlam™

## Pro Gloss

Interlam™ Pro Gloss is a 70µ (2.8 mil) monomeric soft calendared PVC laminating film with a Gloss finish, coated on one side with a pressure sensitive, aqueous acrylic adhesive. Both the film and adhesive contain UV stabilisers, which protect against UV degradation.

- RECOMMENDED FOR INTERIOR AND EXTERIOR USE ON FLEXIBLE MEDIA SUBSTRATES WHERE A GLOSS FINISH IS REQUIRED
- IDEAL FOR POP DISPLAYS, ARCHITECTURAL RENDERINGS, PROMOTIONAL DISPLAYS, AND EVENT SIGNAGE
- INTERLAM™ PRO GLOSS HAS A CLASS 0 FIRE RATING ACCORDING TO UK STANDARDS FOR SURFACE SPREAD OF FLAME, MAKING IT PERFECT FOR APPLICATIONS IN PUBLIC AREAS THAT REQUIRE COMPLIANCE WITH STRICT FIRE REGULATIONS, SUCH AS AIRPORTS, HOTELS AND HOSPITALS.

For more information, performance and warranty guide lines please contact your local Drytac office.

© 2019 Drytac Corporation. E&OE. All other trademarks are the property of their respective owners.

## TECHNICAL SPECIFICATION

### PRODUCT STRUCTURE

<b>Film</b>	Gloss Monomeric Soft Calendared PVC
<b>Adhesive</b>	Acrylic (Pressure Sensitive)
<b>Release Liner</b>	1 Side PE Coated, 1 Side Siliconised Kraft

### PRODUCT CHARACTERISTIC

<b>Film Thickness</b>	2.8 mil (70µ)   3.8 mil
<b>Adhesive Layer</b>	1 mil (25µ)   (95µ)
<b>Film/Adhesive Ratio</b>	2.8:1
<b>UV Protection Factor</b>	Film contains UV stabilisers, which prevent film degradation and provide UV protection to the underlying image
<b>Outdoor Durability</b>	3 Years (Ink Dependent)
<b>Fire Rating</b>	Class 0
<b>Application Temperature</b>	>41°F (20°C)
<b>Service Temperature Range</b>	-13°F to 302°F (-25°C to 150°C)
<b>Peel Strength (20 min, FTM1)</b>	11 N/25mm
<b>Shelf Life</b>	2 Years
<b>Storage Conditions</b>	59°F to 72°F (15°C to 22°C); 50 - 55% Relative Humidity

### PROCESS SETTINGS

Equipment Type & Temperature	Speed
<b>Roller Laminator</b> Room temperature to 104°F (40°C)	1 ft to 8 ft (0.3m to 2.5m) per minute
<b>Press</b>	Not recommended

**DRYTAC®**  
ADHESIVE SCIENCE

#### Europe

Filwood Road,  
Fishponds,  
Bristol, BS16 3RY,  
United Kingdom  
[bristol@drytac.com](mailto:bristol@drytac.com)  
Tel: +44 (0) 117 958 6500

#### Canada

30 Driver Road,  
Brampton,  
Ontario, L6T 5V2,  
Canada  
[toronto@drytac.com](mailto:toronto@drytac.com)  
Tel: +1 800.353.2883

#### USA

5601 Eastport Boulevard,  
Richmond,  
Virginia, 23231,  
USA  
[customerservice@drytac.com](mailto:customerservice@drytac.com)  
Tel: +1 800.280.6013