

MediaShield™

Matte

MediaShield™ Matte is a 3 mil (75µ) plasticised, UV stabilised, clear PVC laminating film with a matte finish, coated on one side with a heat activated solvent acrylic adhesive that is protected by a moisture stable bleached Kraft gridded release paper coated on one side with siliconised PE.

- RECOMMENDED FOR SITUATIONS WHERE A NON-GLARE FINISH IS REQUIRED OR SPECIFIC LIGHTING CONDITIONS CANNOT BE CONTROLLED
- IDEAL FOR IMAGES USED FOR EXHIBITIONS AND POP DISPLAYS THAT WILL BE VIEWED UNDER DIRECT LIGHTING FROM MANY DIFFERENT ANGLES.
- RECOMMENDED FOR PHOTOGRAPHS AND PLAQUE

For more information, performance and warranty guide lines please contact your local Drytac office.

© 2018 Drytac Corporation. E&OE. All other trademarks are the property of their respective owners.

TECHNICAL SPECIFICATION

PRODUCT STRUCTURE

Film	Matte Monomeric Soft Calendared PVC
Adhesive	Solvent Acrylic (Heat Activated)
Release Liner	1 Side PE Coated Bleached Kraft Grid Paper (Moisture Stable)

PRODUCT CHARACTERISTIC

Film Thickness	3 mil (75µ) 4 mil (100µ)
Adhesive Layer	1 mil (25µ)
Film/Adhesive Ratio	3:1
UV Protection Factor	Adhesive contains UV stabilisers, which prevent film degradation and provide UV protection to the underlying image
Outdoor Durability	Not Applicable
Service Temperature Range	-4°F to 203°F (-20°C to 95°C)
Shelf Life	2 Years
Storage Conditions	59°F to 72°F (15°C to 22°C); 50 - 55% Relative Humidity

PROCESS SETTINGS

Equipment Type & Temperature	Speed
Roller Laminator 185°F to 215°F (85°C to 102°C)	1 ft to 8 ft (0.3m to 2.5m) per minute
Press 185°F to 210°F (85°C to 99°C) Dwell Time: 2-8 minutes	

DRYTAC®
ADHESIVE SCIENCE

Europe

Filwood Road,
Fishponds,
Bristol, BS16 3RY,
United Kingdom
bristol@drytac.com
Tel: +44 (0) 117 958 6500

Canada

105 Nuggett Court,
Brampton,
Ontario, L6T 5A9,
Canada
toronto@drytac.com
Tel: +1 800.353.2883

USA

5601 Eastport Boulevard,
Richmond,
Virginia, 23231,
USA
customerservice@drytac.com
Tel: +1 800.280.6013