

OptiTac CF is a 1.75 mil (45µ) high quality, unsupported pressure sensitive, permanent solvent acrylic adhesive, protected by a clear PET release liner on both sides. This carrier free mounting adhesive is made using the finest optical clarity components. OptiTac CF is ideal for reducing silvering when using medias and substrates that may not be completely smooth.

- RECOMMENDED FOR SECOND SURFACE MOUNTING (COMMONLY REFERRED TO AS FACE MOUNTING) OF IMAGES TO CLEAR SUBSTRATES, SUCH AS PETG™, PLEXIGLAS™, ACRYLIC, POLYCARBONATE, AND GLASS
- IDEAL FOR LENTICULAR IMAGING APPLICATIONS, BACKLIT DISPLAY TRANSPARENCIES, TOUCH SCREEN DISPLAYS, AND HIGH QUALITY PHOTOGRAPHIC AND INKJET PRINTED IMAGES
- INDOOR AND SHORT-TERM OUTDOOR USE

For more information, performance and warranty guide lines please contact your local Drytac office.

© 2018 Drytac Corporation. E&OE.
All other trademarks are the property of their respective owners.

TECHNICAL SPECIFICATION

PRODUCT STRUCTURE

Release Liner	Siliconised 1 Side PET
Adhesive	Permanent Solvent Acrylic (Pressure Sensitive)
Release Liner	Siliconised 1 Side PET

PRODUCT CHARACTERISTIC

Film Thickness	Not Applicable
Adhesive Layer	1.75 mil (45µ)
Film/Adhesive Ratio	Not Applicable
UV Protection Factor	Not Applicable
Outdoor Durability	1 Year
Service Temperature Range	-40°F to 212°F (-40°C to 100°C)
Peel Strength (20 min, FTM1)	2000 g/25 mm (glass 24 hours)
Shelf Life	2 Years
Storage Conditions	59°F to 72°F (15°C to 22°C); 50 - 55% Relative Humidity
Shear Strength	0.29 MPa
Transmission	94%
Haze	.04%

PROCESS SETTINGS

Equipment Type & Temperature	Speed
Roller Laminator Room temperature to 104°F (40°C)	1 ft to 8 ft (0.3m to 2.5m) per minute
Press	Not recommended

DRYTAC®
ADHESIVE SCIENCE

Europe

Filwood Road,
Fishponds,
Bristol, BS16 3RY,
United Kingdom
bristol@drytac.com
Tel: +44 (0) 117 958 6500

Canada

105 Nuggett Court,
Brampton,
Ontario, L6T 5A9,
Canada
toronto@drytac.com
Tel: +1 800.353.2883

USA

5601 Eastport Boulevard,
Richmond,
Virginia, 23231,
USA
customerservice@drytac.com
Tel: +1 800.280.6013