

OptiTac is a 1.5 mil (38μ) high quality, optically clear PET film, coated on both sides with a pressure sensitive, permanent solvent acrylic adhesive, both of which are protected by a clear PET release liner. OptiTac is made using the finest optical clarity components. It offers excellent UV stability to graphic prints.

- RECOMMENDED FOR SECOND SURFACE MOUNTING (COMMONLY REFERRED TO AS FACE MOUNTING) OF IMAGES TO CLEAR SUBSTRATES, SUCH AS PETG™, PLEXIGLAS™, ACRYLIC, POLYCARBONATE, AND GLASS
- IDEAL FOR LENTICULAR IMAGING APPLICATIONS, BACKLIT DISPLAY TRANSPARENCIES, TOUCH SCREEN DISPLAYS, AND HIGH QUALITY PHOTOGRAPHIC AND INKJET PRINTED IMAGES
- SUITABLE FOR WINDOW GRAPHICS AND TEMPORARY SIGNAGE
- INDOOR AND SHORT-TERM OUTDOOR USE

For more information, performance and warranty guidelines please contact your local Drytac office.

© 2018 Drytac Corporation. E&OE.  
All other trademarks are the property of their respective owners.

### PRODUCT STRUCTURE

<b>Release Liner</b>	Siliconized 1 Side PET
<b>Adhesive</b>	Permanent Solvent Acrylic (Pressure Sensitive)
<b>Film</b>	Clear PET
<b>Adhesive</b>	Permanent Solvent Acrylic (Pressure Sensitive)
<b>Release Liner</b>	Siliconized 1 Side PET

### PRODUCT CHARACTERISTIC

<b>Film Thickness</b>	1.5 mil (38μ)	3.5 mil (88μ)
<b>Adhesive Layer</b>	1 mil (25μ) on each side	
<b>Film/Adhesive Ratio</b>	1:1.5:1	
<b>UV Protection Factor</b>	UV Stable	
<b>Outdoor Durability</b>	1 Year	
<b>Peel Strength (20 min, FTM1)</b>	15.2 N/25mm (glass 24 hours)	
<b>Service Temperature Range</b>	-40°F to 212°F (-40°C to 100°C)	
<b>Shelf Life</b>	1 Year	
<b>Storage Conditions</b>	59°F to 72°F (15°C to 22°C); 50 - 55% Relative Humidity	

### PROCESS SETTINGS

Equipment Type & Temperature	Speed
<b>Roller Laminator</b> Room temperature to 104°F (40°C)	1 ft to 8 ft (0.3m to 2.5m) per minute
<b>Press</b>	Not recommended

**DRYTAC®**  
ADHESIVE SCIENCE

#### Europe

Filwood Road,  
Fishponds,  
Bristol, BS16 3RY,  
United Kingdom  
bristol@drytac.com  
Tel: +44 (0) 117 958 6500

#### Canada

105 Nuggett Court,  
Brampton,  
Ontario, L6T 5A9,  
Canada  
toronto@drytac.com  
Tel: +1 800.353.2883

#### USA

5601 Eastport Boulevard,  
Richmond,  
Virginia, 23231,  
USA  
customerservice@drytac.com  
Tel: +1 800.280.6013