

Protac™

Scribe™

Protac™ Scribe™ is a 1.6 mil (40µ) biaxially-oriented PP laminating film with a gloss finish, coated on one side with a pressure sensitive, aqueous acrylic adhesive that is protected by a bleached Kraft release paper coated on one side with a siliconized PE.

- SUITABLE FOR APPLICATION TO HEAT SENSITIVE OUTPUT AND HIGH INK COVERAGE IMAGES PRINTED ON PHOTO GLOSS PAPER
- IDEAL FOR DRY ERASE PRESENTATION BOARDS, SCHEDULES, YEARLY PLANNERS, OR MAPS.

For more information, performance and warranty guidelines please contact your local Drytac office.

© 2018 Drytac Corporation. E&OE.
All other trademarks are the property of their respective owners.

TECHNICAL SPECIFICATION

PRODUCT STRUCTURE

Film	Gloss Clear PP
Adhesive	Aqueous Acrylic (Pressure Sensitive)
Release Liner	Siliconized 1 Side PE Coated Kraft

PRODUCT CHARACTERISTIC

Film Thickness	1.6 mil (40µ) 2.6 mil
Adhesive Layer	1 mil (25µ) (65µ)
Film/Adhesive Ratio	1.6:1
UV Protection Factor	Adhesive contains UV stabilizers, which prevent film degradation and provide UV protection to the underlying image
Outdoor Durability	Not Applicable
Service Temperature Range	-4°F to 230°F (-20°C to 110°C)
Peel Strength (20 min, FTM1)	11 N/25mm
Shelf Life	1 year
Storage Conditions	59°F to 72°F (15°C to 22°C); 50 - 55% Relative Humidity

PROCESS SETTINGS

Equipment Type & Temperature	Speed
Roller Laminator Room temperature to 104°F (40°C)	1 ft to 8 ft (0.3m to 2.5m) per minute
Press	Not recommended

DRYTAC®
ADHESIVE SCIENCE

Europe

Filwood Road,
Fishponds,
Bristol, BS16 3RY,
United Kingdom
bristol@drytac.com
Tel: +44 (0) 117 958 6500

Canada

105 Nuggett Court,
Brampton,
Ontario, L6T 5A9,
Canada
toronto@drytac.com
Tel: +1 800.353.2883

USA

5601 Eastport Boulevard,
Richmond,
Virginia, 23231,
USA
customerservice@drytac.com
Tel: +1 800.280.6013