

Overlaminating Film

Clarion™ is a 3 mil (75µ) monomeric soft calendared PVC laminating film with a glossy, lustre or matte finish. These overlaminating films are coated on one side with a pressure sensitive, aqueous acrylic adhesive that is protected by a white clay coated Kraft release paper that is siliconized on the release side.

- GLOSS FINISH IS RECOMMENDED FOR INTERIOR AND EXTERIOR USE ON FLEXIBLE MEDIA SUBSTRATES WHERE A GLOSS FINISH IS REQUIRED
- LUSTRE FINISH IS RECOMMENDED FOR IMAGES THAT WILL BE VIEWED UNDER DIRECT LIGHTING CONDITIONS AND THE LOW SHEEN WITHOUT LOSS OF CONTRAST OR SHARPNESS MAKES CLARION LUSTRE EFFECTIVE FOR A WIDE RANGE OF APPLICATIONS
- MATTE FINISH IS RECOMMENDED FOR INTERIOR AND EXTERIOR USE WHERE A NON-GLARE FINISH IS REQUIRED OR WHERE SPECIFIC LIGHTING CONDITIONS CANNOT BE CONTROLLED
- IDEAL FOR POP DISPLAYS, ARCHITECTURAL RENDERINGS, PROMOTIONAL DISPLAYS, AND EVENT SIGNAGE

For more information,
performance and warranty guide
lines please contact your local
Drytac office.

© 2018 Drytac Corporation. E&OE.
All other trademarks are the property
of their respective owners.

TECHNICAL SPECIFICATION

PRODUCT STRUCTURE

Film	Gloss, Lustre or Matte Monomeric Soft Calendared PVC
Adhesive	Aqueous Acrylic (Pressure Sensitive)
Release Liner	White Clay Coated, 1 Side Siliconized Kraft

PRODUCT CHARACTERISTIC

Film Thickness	3 mil (75µ)
Adhesive Layer	1 mil (25µ)
Film/Adhesive Ratio	3:1
UV Protection Factor	Not Applicable
Outdoor Durability	3 years
Peel Strength (20 min, FTM1)	11 N/25mm
Service Temperature Range	158°F to 203°F (70°C to 95°C)
Shelf Life	1 Year
Storage Conditions	59°F to 72°F (15°C to 22°C); 50 - 55% Relative Humidity

Special Regulatory Information:
This product is formulated to be
compliant with the California Proposition
65 regulation. It contains no zinc, lead,
cadmium, or other heavy metals.
This product is formulated to be
phthalate-free.

DRYTAC[®]
ADHESIVE SCIENCE

Europe

Filwood Road,
Fishponds,
Bristol, BS16 3RY,
United Kingdom
bristol@drytac.com
Tel: +44 (0) 117 958 6500

Canada

105 Nuggett Court,
Brampton,
Ontario, L6T 5A9,
Canada
toronto@drytac.com
Tel: +1 800.353.2883

USA

5601 Eastport Boulevard,
Richmond,
Virginia, 23231,
USA
customerservice@drytac.com
Tel: +1 800.280.6013