

MP07005

TECHNICAL SPECIFICATION

MP07005 is a 5 mil (127 μ) high quality mounting adhesive film. It uses a clear 1 mil (25 μ) polyester film coated on both sides with 2 mil (50.8 μ) pressure sensitive, acrylic adhesive; self wound onto a differential silicone release liner. This mounting adhesive film is custom made using an aggressive hi tack adhesive. Available in various sizes.

A PERMANENT ADHESIVE FOR BONDING VARIOUS SUBSTRATES ESPECIALLY RECOMMENDED FOR:

- LSE (LOW SURFACE ENERGY) MATERIALS AND MOST OTHER DIFFICULT TO BOND TO SURFACES

NOTE: NOT RECOMMENDED FOR USE ON SURFACES THAT COME IN CONTACT WITH SOLVENTS ESPECIALLY KETONES AND ESTERS.

For more information, performance and warranty guide lines please contact your local Drytac office.

© 2018 Drytac Corporation. E&OE.
All other trademarks are the property of their respective owners.

PRODUCT STRUCTURE

Adhesive	Permanent High Tack Acrylic (Pressure Sensitive) 2.0mil (50.8 μ)
Film	Clear Polyester 1.0 mil (25 μ)
Adhesive	Permanent High Tack Acrylic (Pressure Sensitive) 2.0mil (50.8 μ)
Release Liner	Double-sided Siliconized Paper

PRODUCT CHARACTERISTIC

Film Thickness	1 mil (25 μ)	5 mil (127 μ)
Adhesive Layer	2 mil (50.8 μ) + 2 mil (50.8 μ)	
Film/Adhesive Ratio	2:1:2	
Adhesive Type	Permanent Clear	
pH	6	
Heat Resistance Range	-30°C to 140°C (-22°F to 284°F)	
Peel Strength	20 min dwell 24 hrs. dwell	67 ozf/in 66 ozf/in
Shelf Life	2 years	
Storage Conditions	59°F to 72°F (15°C to 22°C); 50 - 55% Relative Humidity	

DRYTAC[®]
ADHESIVE SCIENCE

Europe

Filwood Road,
Fishponds,
Bristol, BS16 3RY,
United Kingdom
bristol@drytac.com
Tel: +44 (0) 117 958 6500

Canada

105 Nuggett Court,
Brampton,
Ontario, L6T 5A9,
Canada
toronto@drytac.com
Tel: +1 800.353.2883

USA

5601 Eastport Boulevard,
Richmond,
Virginia, 23231,
USA
customerservice@drytac.com
Tel: +1 800.280.6013