

## Pro Gloss

Interlam<sup>TM</sup> Pro Gloss is a 3 mil (75µ) monomeric soft calendared PVC laminating film with a Gloss finish, coated on one side with a pressure sensitive, aqueous acrylic adhesive that is protected by a bleached Kraft release paper coated on one side with PE and siliconized on the release side.

- RECOMMENDED FOR INTERIOR AND EXTERIOR USE ON FLEXIBLE MEDIA SUBSTRATES WHERE A GLOSS FINISH IS REQUIRED
- IDEAL FOR POP DISPLAYS, ARCHITECTURAL RENDERINGS, PROMOTIONAL DISPLAYS, EVENT SIGNAGE AND PHOTOGRAPHIC IMAGES

For more information, performance and warranty guidelines please contact your local Drytac office.

© 2025 Drytac Corporation. E&OE.  
All other trademarks are the property of their respective owners.

## TECHNICAL SPECIFICATION

### PRODUCT STRUCTURE

Film	Gloss Monomeric Soft Calendared PVC
Adhesive	Acrylic (Pressure Sensitive)
Release Liner	1 Side PE Coated, 1 Side Siliconised Kraft

### PRODUCT CHARACTERISTIC

Film Thickness	3.0 mil (75µ)   4.0 mil (100µ)
Adhesive Layer	1 mil (25µ)   (100µ)
Film/Adhesive Ratio	2.8:1
UV Protection	Yes
Outdoor Durability	5 Years (Ink Dependent)
Fire Rating	Class 0
Application Temperature	-4°F (-20°C)
Service Temperature Range	-49°F to 230°F (-45°C to +110°C)
Peel Strength (20 min, FTM1)	11 N/25mm
Shelf Life	2 years
Storage Conditions	59°F to 72°F (15°C to 22°C); 50 - 55% Relative Humidity

### PROCESS SETTINGS

Equipment Type & Temperature	Speed
Roller Laminator Room temperature to 104°F (40°C)	1 ft to 8 ft (0.3m to 2.5m) per minute
Press	Not recommended

**DRYTAC<sup>®</sup>**  
ADHESIVE SCIENCE

#### Europe

Filwood Road,  
Fishponds,  
Bristol, BS16 3RY,  
United Kingdom  
[bristol@drytac.com](mailto:bristol@drytac.com)  
Tel: +44 (0) 117 958 6500

#### Canada

30 Driver Road,  
Brampton,  
Ontario, L6T 5V2,  
Canada  
[toronto@drytac.com](mailto:toronto@drytac.com)  
Tel: +1 800.353.2883

#### USA

5401 B Eubank Road,  
Sandston,  
Virginia, 23150,  
USA  
[customerservice@drytac.com](mailto:customerservice@drytac.com)  
Tel: +1 800.280.6013